





















Astra F.R. dis. Frida
























AST/FRI



Name	Cat.	Ref.	 Composition	 F.R. classification	 Health certifications	 Width cm	 Weight g/m2	 Thickness mm	 OF %	 Shading	 TS %	 RS %	 AS %	 TL %	 RL %	 INT Type C glass	 EXT Type C glass	 INT Type D glass	 EXT Type D glass	 Glare control	 ↓UV %	 αW	Mechanical resistance WARP daN/5cm	Mechanical resistance WEFT daN/5cm	Colour fastness to light	OUTDOOR	Sealable
Reference Standard							UNI EN ISO 2286-2	UNI EN ISO 2286-3	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	EN ISO 11654	UNI EN ISO 1421	UNI EN ISO 1421	UNI EN ISO 105 B02		

Frida F.R.	ASTFRI	AST/FRI	100% PL Trevira CS	Classe1 (I), M1(F), B1(D), BS (GB), EN 13773 Class1(EU)	OEKO-TEX REACH	230	170	0,35	15	○	43	50	7	45	54	0,41						90					6/7	
-------------------	--------	---------	--------------------	---	-------------------	-----	-----	------	----	---	----	----	---	----	----	------	--	--	--	--	--	----	--	--	--	--	-----	--

All coefficients have a possible tolerance of +/- 5%
Attention: colour shades may vary slightly from one dye lot to another

	Width		Composition		Health certification		IMO - Fabrics for marine industry		Solar reflection		Light absorption		Sound absorption
	Thickness		Flame retardant		Colour fastness		Openess factor		Solar absorption		G tot Type C - GLASS		Warp - Weft N5 cm
	Weight		Transparency		Sealable		Solar transmission		Light transmission		UV reduction		Glare control

MAINTENANCE REMOVE THE BLIND FROM THE SYSTEM, ROLL NO FOLDING. SOAK IN WARM WATER MAX 30° WITH DELICATE DETERGENT (E.G. IN A BATH TUB). MARKS AND DUST CAN BE REMOVED WITH A SOFT BRUSH. RINSE CLOTH THOUROUGHLY WITH WATER AND DRAIN. HANG THE FABRIC WHILE DAMP AND LEAVE TO DRY. CAN BE IRONED AT SETTING 1.