


























Cristal GKS FUME' 45
























KS/45-140



Name	Cat.	Ref.	 Composition	 F.R. classification	 Health certifications	 Width cm	 Weight g/m2	 Thickness mm	 OF %	 Shading	 TS %	 RS %	 AS %	 TL %	 RL %	 INT Type C glass	 EXT Type C glass	 INT Type D glass	 EXT Type D glass	 Glare control	 UV %	 αw	 Mechanical resistance WARP daN/5cm	 Mechanical resistance WEFT daN/5cm	 Colour fastness to light	 OUTDOOR	 Sealable
Reference Standard							UNI EN ISO 2286-2	UNI EN ISO 2286-3	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	EN ISO 11654	UNI EN ISO 1421	UNI EN ISO 1421	UNI EN ISO 105 B02		

Cristal GKS FUME' 45	GKS	KS/45-140	100% PVC	Classe 2 (I)		140	560	0,45			52	6	42	47	6		0,33							220	200		✓	heat
----------------------	-----	-----------	----------	--------------	---	-----	-----	------	--	--	----	---	----	----	---	--	------	--	--	--	--	--	--	-----	-----	--	---	------

All coefficients have a possible tolerance of +/- 5%
 Attention: colour shades may vary slightly from one dye lot to another

	Width		Composition		Health certification		IMO - Fabrics for marine industry		Solar reflection		Light absorption		Sound absorption
	Thickness		Flame retardant		Colour fastness		Openess factor		Solar absorption		G tot Type C - GLASS		Warp - Weft N5 cm
	Weight		Transparency		Sealable		Solar transmission		Light transmission		UV reduction		Glare control

MAINTENANCE TO REMOVE DIRT AND DUST, WE RECOMMEND THE USE OF THE CLEANING PRODUCT APCO CRISTAL PLUS, FOLLOWED BY APCO CRISTALPLUS LUBRILUX AFTER WASHING. THE USE OF WATER IS ALLOWED, BUT ONLY USA A GENTLE SETTING ON A PRESSURE WASHER. ALLOW TO DRY BEFORE ROLLING UP OR FOLDING.