


Cristal KS 50 F.R.























KS/50-140



Ref.	 cm	 mm	 g/m ²												EXT
KS/50-140	140	0,50	610	100% PVC	Classe 1(I), M2(F), Cs3d0 (EU)	Transparent	RECYCLABLE	heat	No	85	8	7	89	8	0,57

All coefficients have a possible tolerance of +/- 5%
Attention: colour shades may vary slightly from one dye lot to another

 Width	 Composition	 Health certification	 IMO - Fabrics for marine industry	 Solar reflection	 Light absorption	 Sound absorption
 Thickness	 Flame retardant	 Colour fastness	 Openess factor	 Solar absorption	 G tot Type C - GLASS	 Warp - Weft N5 cm
 Weight	 Transparency	 Sealable	 Solar transmission	 Light transmission	 UV reduction	

MAINTENANCE TO REMOVE DIRT AND DUST, WE RECOMMEND THE USE OF THE CLEANING PRODUCT APCO CRISTAL PLUS, FOLLOWED BY APCO CRISTALPLUS LUBRILUX AFTER WASHING. THE USE OF WATER IS ALLOWED, BUT ONLY USA A GENTLE SETTING ON A PRESSURE WASHER. ALLOW TO DRY BEFORE ROLLING UP OR FOLDING.