



Lavanda Plì 20mm




TP/3910/01




TP/3910/02




TP/3910/03




TP/3910/04



TP/3910/05



TP/3910/06



Name	Cat.	Ref.	Composition	F.R. classification	Health certifications	Width cm	Weight g/m2	Thickness mm	OF %	Shading	TS %	RS %	AS %	TL %	RL %	INT Type C glass	EXT Type C glass	INT Type D glass	EXT Type D glass	Glare control	↓UV %	αω	Mechanical resistance WARP daN/5cm	Mechanical resistance WEFT daN/5cm	Colour fastness to light	OUTDOOR	Sealable	
Reference Standard							UNI EN ISO 2286-2	UNI EN ISO 2286-3	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	EN ISO 11654	UNI EN ISO 1421	UNI EN ISO 1421	UNI EN ISO 105 B02		

Lavanda Pli 20mm	LAV	TP/3910/01	100% PL	OEKO-TEX	225	170	0,35	4	○	34	48	18	29	44	0,42						84					5/7		
Lavanda Pli 20mm	LAV	TP/3910/02	100% PL		225	170	0,35	4	○	25	39	36	23	38	0,44						87					5/7		
Lavanda Pli 20mm	LAV	TP/3910/03	100% PL		225	170	0,35	4	○	28	43	29	27	42	0,43						84					5/7		
Lavanda Pli 20mm	LAV	TP/3910/04	100% PL		225	170	0,35	4	○	23	40	37	21	38	0,44						88					5/7		
Lavanda Pli 20mm	LAV	TP/3910/05	100% PL		225	170	0,35	4	○	22	32	46	18	29	0,47						89					5/7		
Lavanda Pli 20mm	LAV	TP/3910/06	100% PL		225	170	0,35	4	○	19	33	48	18	32	0,46						89					5/7		

All coefficients have a possible tolerance of +/- 5%
 Attention: colour shades may vary slightly from one dye lot to another

Width	Composition	Health certification	IMO - Fabrics for marine industry	Solar reflection	Light absorption	Sound absorption
Thickness	Flame retardant	Colour fastness	Openess factor	Solar absorption	G tot Type C - GLASS	Warp - Weft N5 cm
Weight	Transparency	Sealable	Solar transmission	Light transmission	UV reduction	Glare control

MAINTENANCE DO NOT USE WATER: INTERVENE USING DRY METHODS FOR REMOVING DUST DEPOSITS.