



Screen P43 F.R.



P/430-300



P/431-300




P/432-300



P/433-300



P/434-300




P/435-300



P/436-300



P/437-300



Name	Cat.	Ref.	 Composition	 F.R. classification	 Health certifications	 Width cm	 Weight g/m2	 Thickness mm	 OF %	 Shading	 TS %	 RS %	 AS %	 TL %	 RL %	 INT Type C glass	 EXT Type C glass	 INT Type D glass	 EXT Type D glass	 Glare control	 ↓UV %	αw	Mechanical resistance WARP daN/5cm	Mechanical resistance WEFT daN/5cm	Colour fastness to light	OUTDOOR	Sealable
Reference Standard							UNI EN ISO 2286-2	UNI EN ISO 2286-3	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	EN ISO 11654	UNI EN ISO 1421	UNI EN ISO 1421	UNI EN ISO 105 B02		

Screen P43 F.R.	P43	P/430-300	30% PL 70% PVC	Classe 1 (I), NFPA 701 (US), BS (GB)	 FUNGISTATIC GREENGUARD GOLD OEKO-TEX REACH	300	440	0,56	3		19	74	7	15	84	0,33	0,13	0,24	0,09	1	94	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/431-300	30% PL 70% PVC			300	440	0,56	3		18	72	10	15	82	0,34	0,13	0,25	0,09	1	95	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/432-300	30% PL 70% PVC			300	440	0,56	3		19	57	24	13	64	0,39	0,15	0,26	0,10	1	96	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/433-300	30% PL 70% PVC			300	440	0,56	3		9	43	48	6	48	0,43	0,08	0,27	0,08	3	97	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/434-300	30% PL 70% PVC			300	440	0,56	3		8	36	56	5	39	0,45	0,10	0,28	0,08	3	96	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/435-300	30% PL 70% PVC			300	440	0,56	3		6	7	87	5	7	0,54	0,12	0,30	0,10	3	95	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/436-300	30% PL 70% PVC			300	440	0,56	3		5	9	86	5	10	0,54	0,11	0,30	0,09	3	95	0,15	140	140	8	✓	heat
Screen P43 F.R.	P43	P/437-300	30% PL 70% PVC			300	440	0,56	3		5	4	91	5	4	0,56	0,11	0,31	0,10	4	95	0,15	140	140	8	✓	heat

All coefficients have a possible tolerance of +/- 5%
Attention: colour shades may vary slightly from one dye lot to another

Width

Composition

Health certification

IMO - Fabrics for marine industry

Solar reflection

Light absorption

Sound absorption

Thickness

Flame retardant

Colour fastness

Openess factor

Solar absorption

G tot Type C - GLASS

Warp - Weft N5 cm

Weight

Transparency

Sealable

Solar transmission

Light transmission

UV reduction

Glare control

MAINTENANCE HANDLE THE FABRIC WITH CARE, USING CLEAN DRY HANDS. DO NOT USE SOLVENTS OR ANY ABRASIVE SUBSTANCES THAT MAY DAMAGE THE FABRIC. WHEN CLEANING WINDOWS THE BLIND MUST BE RAISED TO AVOID ANY DIRECT OR INDIRECT SPRAY OF CLEANING PRODUCTS. REMOVE THE DUST WITH A VACUUM CLEANER OR USING COMPRESSED AIR, AVOID PULLING OR STRETCHING FABRIC. ONLY FOR PVC COATED PRODUCTS, CLEAN WITH A DAMP CLOTH OR A SPONGE DIPPED IN SOAPY WATER IF NECESSARY. RINSE WITH CLEAN WATER. DO NOT RUB. LEAVE THE BLIND DOWN UNTIL COMPLETELY DRY.