


Venus BLO F.R. Plì 20mm



TP/3960/01



TP/3960/02















TP/3960/03
























TP/3960/04



Name	Cat.	Ref.	 Composition	 F.R. classification	 Health certifications	 Width cm	 Weight g/m2	 Thickness mm	 OF %	 Shading	 TS %	 RS %	 AS %	 TL %	 RL %	 INT Type C glass	 EXT Type C glass	 INT Type D glass	 EXT Type D glass	 Glare control	 ↓UV %	 αω	 Mechanical resistance WARP daN/5cm	Mechanical resistance WEFT daN/5cm	Colour fastness to light	OUTDOOR	Sealable
Reference Standard							UNI EN ISO 2286-2	UNI EN ISO 2286-3	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	UNI EN 14501	EN ISO 11654	UNI EN ISO 1421	UNI EN ISO 1421	UNI EN ISO 105 B02		

Venus BLO F.R. Pli 20mm	VENUB	TP/3960/01	100% PL	Classe 1 (I)	OEKO-TEX REACH	305	243	0,18		0	71	29	0	71	0,34							100					4/5			
Venus BLO F.R. Pli 20mm	VENUB	TP/3960/02	100% PL	Classe 1 (I)		305	243	0,18		0	71	29	0	71	0,34								100					4/5		
Venus BLO F.R. Pli 20mm	VENUB	TP/3960/03	100% PL	Classe 1 (I)		305	243	0,18		0	71	29	0	71	0,34								100					4/5		
Venus BLO F.R. Pli 20mm	VENUB	TP/3960/04	100% PL	Classe 1 (I)		305	243	0,18		0	71	29	0	71	0,34								100					4/5		

All coefficients have a possible tolerance of +/- 5%
Attention: colour shades may vary slightly from one dye lot to another

 Width	 Composition	 Health certification	 IMO - Fabrics for marine industry	 Solar reflection	 Light absorption	 Sound absorption
 Thickness	 Flame retardant	 Colour fastness	 Openess factor	 Solar absorption	 G tot Type C - GLASS	 Warp - Weft N5 cm
 Weight	 Transparency	 Sealable	 Solar transmission	 Light transmission	 UV reduction	 Glare control

MAINTENANCE DO NOT USE WATER: INTERVENE USING DRY METHODS FOR REMOVING DUST DEPOSITS.